


acclaim LV

Laminated Flexible Packaging Film

DESCRIPTION	This structure is a flexible film construction for lidding applications that require moderately high OTR and WVTR barrier levels for Modified Atmosphere Packaging (MAP). Sealant with provides excellent seals.
STRUCTURE	PvDC coated PET 48GA/Ink/ADH/LDPE 2.4mil
LAMINATION	100% Solids Solventless Adhesive method
PACK	Rolls wrapped in poly bags capped with core plugs.
PRINT	Rotogravure, up to 10 colors, PvDC side of PET.



FILM SPECIFICATIONS

Gauge (+/- 5%)	300
Seal Strength (at 270°F g/in 30 PSI, ½ Sec.)	>1200
Yield (Square Inches/Lb)	8,751
O ₂ TR (cc/100 sq in/24Hrs)	<.5
WVTR (g/100 sq in/24 HRS @ 100°F @90% RH)	≤0.222
Haze (%)	7.0
Seal Range	225°F- 275°F
Gloss(20°C)	140

©accent Flexibles LLC To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. Accent Flexibles LLC does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations, regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document.