


# acclaim PP

## Laminated Packaging Film

<b>DESCRIPTION</b>	This structure is a flexible film construction for food products that require moderate OTR and WVTR barrier levels. Has good sealing properties and excellent clarity.
<b>STRUCTURE</b>	Co-extruded OPP 70GA/Ink/ADH/Co-extruded OPP 70GA
<b>LAMINATION</b>	100% Solids Solventless Adhesive method
<b>PACK</b>	Rolls wrapped in poly bags capped with core plugs.
<b>PRINT</b>	Rotogravure, up to 10 colors, ink trapped between the film layers



### FILM SPECIFICATIONS

Gauge (+/- 5%)	165
Seal Strength (at 270°F g/in 30 PSI, ½ Sec.)	>800
Gloss (45°)	90
WVTR (g/100 sq in/24 HRS @ 100°F @90% RH)	<0.25
Haze (%)	3.6-4.8
Seal Temperature	257°F
Tensile Strength MD	>19,000 PSI

©accent Flexibles LLC To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. Accent Flexibles LLC does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations, regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document.